

Local Name	torem, sawai, kayu sawo, sabo (Indonesia), manilkara (Papua New Guinea)	
Botanical Name	<i>Manilkara kanosiensis</i> H. J. Lam & B. J. D. Meeuse	
Family	Sapotaceae	
Classification	Hardwood	
Distribution	Indonesia (Maluku), Papua New Guinea (Bismark archipelago)	
General Description	The colour of heartwood is red-brown weathering to a dark red-brown, and the colour of sapwood is more lighter. The surface of wood is shiny and smooth. And it has straight and interlocking grains. Although is very hard wood and it easy to dry, but can cause crack surface.	
Physical Properties	Air-Dry Density	1.01 - 1.15 kg/m ³
	Shrinkage Radial	5 - 5.9 %
	Shrinkage Tangential	6 - 7 %
	Recommended Kiln Schedule	n.a
Strength Class	Bending Strength (MPa)	> 156.7
	Compression Strength	-
Durability Class	In Contact to damp ground Influenced only by water, but kept away from water and enough air Below the roof, not in contact with damp ground and enough air Below the roof, not in contact with damp ground and enough air, take care in good manner and painted regularly. Termite attack Wood powder attack	
Uses	Used to create sculpture, furniture, carpentry tools, windmills, poles, etc	

Picture :





f sapwood is
light, wavy
ack on

m³

-
-
-
-

no
no



|